

HETROGENEOUS FLOORING


CLASSIC+




Jeoflor
AUSTRIA



34-43



0201 Bruyere



0210 Jais




0232 Pine




0233 Tea




0234 Egg




0235 Sky



0236 Grass



0237 Pink



0238 Kumquat



0239 Lite Grey



0307 Ciel




0243 Beige




0303 Chocolat



0312 Ruby



0240 Dark Grey



0501 Yellow Grey-Walnut



0245 Mild Beige-Compose

TECHNICAL SPECIFICATIONS

CLASSIC+

DESCRIPTION			
Total thickness	ISO 24346 (EN 428)	mm	2.0*
Wearlayer thickness	ISO 24340 (EN 429)	mm	0.3
Weight	ISO 23997 (EN 430)	g/m ²	3150
Width of sheet	ISO 24341 (EN 426)	lm	20
Length of sheet	ISO 24341 (EN 426)	lm	
CLASSIFICATION			
Norm / Product specification	-	-	ISO 10582 (EN 649)
European classification	ISO 10874 (EN 685)	class	Bfl-s1
Fire rating	EN 13501 - 1	class	<2
Static electrical propensity	EN 1815	kV	R10
Slip resistance wet	DIN 51 130	class	
PERFORMANCES			
Type binder content	ISO 10582	type	≤ 0.4
Dimensional stability	ISO 23999 (EN 434)	%	≤ 0.1
Residual indentation	ISO 24343-1 (EN 433)	mm	OK
Castor chair test	ISO 4918 (EN 425)	-	0.25
Thermal conductivity	ISO 10456 (EN 12524)	W/(m.k)	≥ 6
Colour fastness	ISO 105 - B02	degree	OK
Chemical product resistance	ISO 26987 (EN 423)	-	Pur+ Protected
Surface treatment	-	-	>99% inhibits growth
Anti-bacterial activity (E.coli - S.aureus - MRSA)	JIS Z 2801	-	99.7% after 5h
Antiviral activity (human coronavirus 229E)	ISO 21702	-	
ENVIRONMENT / INDOOR AIR QUALITY			
TVOC after 28 days	ISO 16000 - 6	µg/m	<100
CE MARKING			
		    	

The implementation of an effective cleaning regime is the most important defence against infections.

Be connected!



#Jeoflor



Our related products!



Floor
Self Leveling



Wall Coverings
& Protections



Skirting &
Profiles



Handrails



LCA

Eco-designed according to a product specific Life Cycle Analysis



WELLNESS

Walking comfort < 75 dB



COMPOSITION

100% REACH compliant



INDOOR AIR QUALITY

TVOC emissions 100 times better than norm requirements (TVOC < 10 µg/m³ after 28 days)



RECYCLABILITY

100%



RECYCLED CONTENT

25%

Jeoflor

Alptahls GmbH, Bürgergasse 4, 8330 Feldbach, Austria. =

Tel. +43 (0)3152 370 49

info@jeoflor.com www.jeoflor.com

Toll Free : 18002028498

